

Razeen® LR 1150

Unmodified, medium viscosity liquid Epoxy Resin



Applications Razeen® LR 1150 is suitable for the formulation of solvent-free coatings, flooring screeds, toweling compounds, etc. when cured with polyamines, polyamidoamines or their adducts.

Properties General purpose, liquid Araldite epoxy resin. Excellent mechanical properties and resistance to chemicals, which can be modified within wide limits by using various hardeners and fillers.

Specific key data	Property	Value	Test method
	Appearance	Clear, No Contamination	JCTM 001
	Color Gardner	2 max	ASTM D-1544
	Epoxy Value	0.530 – 0.546 eq/100g	ASTM D-1652
	Weight per epoxide	183 – 189 g/eq	ASTM D-1652
	Hydrolyzable Chlorine	400 ppm max	JCTM-195
	Viscosity @ 25°C (77°F)	10000 – 12000 mPa.s	ISO 9371:1990E

Specific key data are individually checked throughout, guaranteed and included in certificate of analysis.

Typical Key Data	Property	Value	Test method
	Density at 25°C	1.17 g/cm ³	ISO 1675
	Flash point	≥ 200 °C	ISO 2719

Typical key data are spot-checked; the values are typical for the product and are indicated for information only. The values are not guaranteed or included in the certificate of analysis.

As-supplied form	Liquid
Odor	none
Self life (at storage temperature between 2-40°C) (See expiry date on original container)	Several Years
Hazardous decomposition products (when disposed of in fire)	Carbon monoxide, carbon dioxide, and other toxic gases and vapors
Disposal	Regular procedures approved by local authorities

Packaging & Storage Razeen[®] LR 1150 is supplied in bulk and in 240 kg steel drums. Araldite GY 250 should be stored in a dry place, preferably in the sealed original container, at temperature between 2 °C and 40 °C (temperatures will never be allowed to drop under 0 °C). The product should not be stored exposed to direct sunlight.

Razeen[®] LR 1150 may crystallize if stored for protracted periods under certain conditions. If this occurs, it can be restored to its original condition by heating it to 70-80 °C and stirring it thoroughly.

Handling/Safety Precautions Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product safety data sheets.

Note Razeen[®] is a registered trademark of JANA or an affiliate thereof.

Jubail Chemical Industries Co. (JANA)
P.O Box 10661
Jubail Industrial city 31961
Kingdom of Saudi Arabia
Tel : +966 3 3585002
Fax : +966 3 3585113
Website : www.jana-ksa.net

DISCLAIMER:

THE INFORMATION AND RECOMMENDATIONS CONTAINED HEREIN ARE BASED UPON OUR DATA BELIEVED TO BE CORRECT. HOWEVER, SINCE THE CONDITION OF USE ARE BEYOND OUR CONTROL, NO GUARANTEE OR WARRANTY OF ANY KIND OF EXPRESSED OR IMPLIED IS MADE WITH RESPECT TO THE INFORMATION CONTAINED HEREIN.