



Razeen® LR 2254

Modified liquid Epoxy Resin

General Razeen® LR 2254 is a low viscose epoxy resin based on bisphenol A and modified with an aliphatic monoglycidyl ether.

Applications Razeen® LR 2254 can be cured with polyamines, polyamidoamines or their adducts in order to formulate solvent free coatings, self-leveling and mortar floors, concrete injections, structure adhesives, trowelling compounds and impregnation systems. In combination with unmodified epoxy resins like Razeen® LR 1100 or LR 1150 the viscosity of the end formulation can be adjusted. The Razeen® LR 2254 is FDA approved and therefore a most ideal resin for coatings and flooring systems applied in food processing rooms or warehouses.

Properties Due to the low viscosity Razeen® LR 2254 is most suitable for the formulation of solvent free coatings and flooring systems which show the following performance:

- Best diluting effect of all reactive diluents
- Good penetration into concrete surface
- FDA approved and therefore when fully cured ideal to be used in contact with food

Specific key data	Property	Value	Test method
	Appearance	Clear, No Contamination	JCTM 001
	Color APHA	125 max.	ASTM D-1209
	Epoxy Value	4.76 - 5.26 eq/kg	ASTM D-1652
	Weight per epoxide	190 - 210 g/eg	ASTM D-1652
	Viscosity @ 25°C (77°F)	600 - 1200 mPa.s	ISO 12058-1

Specific key data are individually checked thought, guaranteed, and included in the certificates of analysis.

Typical key data	Property	Value	Test method
	Density at 25°C	1.11 g/cm ³	ISO 1675
	Flash point	≥ 150 °C	ISO 2719

Typical key data are spot-checked; the values are typical for the product and are indicated for information only. The values are not included in certificate of analysis.

As-supplied form	Liquid
Odor	Yes
Self life (at storage temperature between 2 - 40°C) (See expiry date on original container)	Several Years
Hazardous decomposition products	Carbon monoxide, carbon dioxide, nitrogen oxides and other toxic gases and vapors
Disposal	Regular procedures approved by local authorities

Packaging & Storage	Razeen® LR 2254 is supplied in bulk and in 220 kg. steel drums. This product should be stored in a dry place, preferably in the sealed original container; at temperatures between 2°C and 40°C. The product should not be stored exposed to direct sunlight. Razeen® LR 2254 could slightly crystallize if stored at low temperature (below 2°C). If this occurs it can be restored to its condition by heating up to 60 - 70°C under stirring.
Handling Precautions	Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product safety data sheets.
Note	Razeen® is a registered trademark of JANA or an affiliate thereof.

Jubail Chemical Industries Co. (JANA)
P.O Box 10661
Jubail Industrial city 31961
Kingdom of Saudi Arabia
Tel : +966 3 3585002
Fax : +966 3 3585113
Website : www.jana-ksa.net

ISO 9001 : 2000



0010737-1044329

DISCLAIMER:

THE INFORMATION AND RECOMMENDATIONS CONTAINED HEREIN ARE BASED UPON OUR DATA BELIEVED TO BE CORRECT. HOWEVER, SINCE THE CONDITION OF USE ARE BEYOND OUR CONTROL, NO GUARANTEE OR WARRANTY OF ANY KIND OF EXPRESSED OR IMPLIED IS MADE WITH RESPECT TO THE INFORMATION CONTAINED HEREIN.