

# Razeen® SR 5357

## Solid Epoxy Resin based on Bisphenol A and Novolak



<b>General</b>	Solid epoxy resin based on bisphenol A and phenol novolak for powder coating.
<b>Applications</b>	Razeen® SR 5357 is a high melt viscosity epoxy novolak modified solid epoxy resin suited for the manufacture of functional coating powders. The resin is mainly used as an up grader in combination with unmodified Bisphenol-A epoxy resins from "type 3-4".
<b>Properties</b>	<ul style="list-style-type: none"> <li>• Depending on hardener used Razeen® SR 5357 shows:</li> <li>• Lower temperature cure</li> <li>• Excellent mechanical and electrical properties</li> <li>• Good corrosion and chemical resistance</li> <li>• High gloss for decorative applications</li> <li>• Excellent adhesion</li> <li>• And excellent edge coverage</li> <li>• FDA approved.</li> </ul>

Specific key data	Property	Value	Test method
	Appearance	Clear, no contamination	JCTM 002
	Color Gardner*	2 max	ASTM D-1544
	Epoxy value	0.117 - 0.129 eq/100gms	ASTM D-1652
	Weight per epoxide	775 - 855 g/eq	ASTM D-1652
	Viscosity (ICI cone & plate @ 200°C)	2400 - 3700 mPa.s	ASTM D-4440

\*40% in butyl carbitol

*Specific key data are individually checked throughout, guaranteed and included in Certificate of Analysis.*

Typical Key Data	Property	Value	Test method
	Softening point (Mettler)	≈110 °C	DIN 51920
	Density at 25°C	1.19 g/cm <sup>3</sup>	ISO 8130
	Flash point	≥ 200 °C	ISO 2592

*Typical key data are spot-checked, the values are typical for the product and are indicated for information only. The values are not included in certificate of analysis.*

As-supplied form	flakes (< 5 mm sieve)
Odor	none
Self life (at storage temperature between 2-40°C) (See expiry date on original container)	Several Years
Hazardous decomposition products (when disposed of in fire)	Carbon monoxide, carbon dioxide, nitrogen oxides and other toxic gases and vapors
Disposal	Regular procedures approved by local authorities

---

**Package and Storage** Razeen® SR 5357 is available in 25 Kg. bags. This product should be stored in a dry place, preferably in the sealed original container at temperatures between 2°C and 40°C (temperatures will never be allowed to drop under 0°C). The product should not be stored exposed to direct sunlight.

---

**Handling/Safety Precautions** Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product safety data sheets.

Forced ventilation and dust masks or respirators should be used in order to ensure that operatives do not breath in dust generated by resin, hardener or formulated powder coatings.

---

**Note** Razeen® is a registered trademark of JANA or an affiliate thereof.

Jubail Chemical Industries Co. (JANA)  
P.O Box 10661  
Jubail Industrial city 31961  
Kingdom of Saudi Arabia  
Tel : +966 3 3585002  
Fax : +966 3 3585113  
Website : [www.jana-ksa.net](http://www.jana-ksa.net)

**DISCLAIMER:**

THE INFORMATION AND RECOMMENDATIONS CONTAINED HEREIN ARE BASED UPON OUR DATA BELIEVED TO BE CORRECT. HOWEVER, SINCE THE CONDITION OF USE ARE BEYOND OUR CONTROL, NO GUARANTEE OR WARRANTY OF ANY KIND OF EXPRESSED OR IMPLIED IS MADE WITH RESPECT TO THE INFORMATION CONTAINED HEREIN.