



Razeen® SR 5357

Solid Epoxy Resin based on Bisphenol A and Novolac

General	Solid epoxy resin based on bisphenol A and phenol novolac for powder coating		
Applications	Razeen® SR 5357 is a high melt viscosity epoxy novolac modified solid epoxy resin suited for the manufacture of powder coatings. The resin is mainly used to improve performance in combination with unmodified Bisphenol-A epoxy resins from type 3 – 4, enhancing corrosion and chemical resistance. Such coatings are suitable for rebar (concrete reinforcement) and pipe applications.		
Properties	Depending on hardener used Razeen® SR 5357 based coatings show: <ul style="list-style-type: none"> • Low temperature cure (high reactivity) • Excellent electrical properties • Good corrosion resistance • Excellent chemical and heat resistance • Excellent edge coverage • Good adhesion • Meet the requirements of the FDA 		
Specific key data	Property	Value	Test method
	Appearance	Clear, no contamination	JCTM 002
	Color Gardner*	2 max	ASTM D-1544
	Epoxy value	1.17 – 1.29 eq/Kg	ASTM D-1652
	Weight per epoxide	775 - 855 g/eq	ASTM D-1652
	Melt viscosity at 200°C	2400 - 3700 mPa.s	ASTM D-4440
	<i>Specific key data are individually checked throughout, guaranteed and included in Certificate of Analysis.</i>		
Typical Key Data	Viscosity @ 25 °C (77 °F)*	1000 - 1600 mPa.s	ISO 12058-1
	Softening point (Mettler)	~110 °C	ASTM D-3461
	Density at 25°C	1.19 g/cm ³	ISO 8130
	Flash point	≥ 200 °C	ISO 2592
	<i>*40% in butyl carbitol</i>		
	<i>Typical key data are spot-checked, the values are typical for the product and are indicated for information only. The values are not included in certificate of analysis.</i>		
	As-supplied form	Flakes (< 5 mm sieve)	
	Odor	None	
	Shelf life (at storage temperature between 2-40°C) (See expiry date on original container)	Several years	
	Hazardous decomposition products (when disposed of in fire)	Carbon monoxide, carbon dioxide, nitrogen oxides and other toxic gases and vapors.	
	Disposal	Regular procedures approved by local authorities.	

Package & Storage	Razeen® SR 5357 is supplied in 25 Kg. bags. This product should be stored in a dry place, preferably in the sealed original packaging at temperatures between 2°C and 40°C. The product should not be stored exposed to direct sunlight.
Handling/Safety Precautions	Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product safety data sheets. Forced ventilation and dust masks or respirators should be used in order to ensure that operatives do not breath in dust generated by resin, hardener or formulated powder coatings.
Note	Razeen® is a registered trademark of JANA or an affiliate thereof.

Jubail Chemical Industries Co. (JANA)
P.O Box 10661
Jubail Industrial city 31961
Kingdom of Saudi Arabia
Tel : +966 3 3478888
Fax : +966 3 3476705
Website : www.jana-ksa.net

ISO 9001 : 2000



0010737-1044329

DISCLAIMER:

THE INFORMATION AND RECOMMENDATIONS CONTAINED HEREIN ARE BASED UPON OUR DATA BELIEVED TO BE CORRECT. HOWEVER, SINCE THE CONDITION OF USE ARE BEYOND OUR CONTROL, NO GUARANTEE OR WARRANTY OF ANY KIND OF EXPRESSED OR IMPLIED IS MADE WITH RESPECT TO THE INFORMATION CONTAINED HEREIN.